

Tyfo® SEP

(Spray Elasto-Plastic)

DESCRIPTION

Tyfo® SEP is a urethane-urea base, two-component system. This system is spray-applied and cures as a rubber-like material. The material is used for coating and protecting surfaces. Carbon, glass or aramid fabrics are applied for optimum performance.

USE

Walls, columns, beams, slabs, and steel elements for environmental protection systems.

ADVANTAGES

- Durable coating for cementitious, metal, wood and/or composite surfaces
- Good high temperature properties
- Excellent adhesion to most materials
- High elongation
- Ambient cure
- 100% solvent-free

COVERAGE

Depends on applied thickness. The material will fill small voids and uneven surfaces.

PACKAGING

Tyfo® SEP is packaged in two 5-gallon (19L) or two 15-gallon (56L) containers for smaller applications. Also available in 55-gallon (208L) drums for larger applications. Fabrics are shipped as part of the package.

MIX RATIO

100 parts of component A to 100 parts of component B by volume.

SHELF LIFE

Two years in original, unopened and properly stored containers.

STORAGE CONDITIONS

The material must be stored in a 70° to 90° F (21 to 32° C) temperature range. Avoid freezing.

CERTIFICATE OF COMPLIANCE

- Will be supplied upon request, complete with state and federal packaging laws with copy of labels used.
- Material safety data sheets will be supplied upon request.
- Possesses 0% V.O.C. level per RSTM B-2369.

HOW TO USE THE TYFO® SEP SYSTEM

INSTALLATION

Tyfo® SEP System is to be installed by Fyfe Co. LLC trained and certified applicators.

SURFACE PREPARATION

The required surface preparation is largely dependent on the type of element to which the material is being applied.

MIXING

The mixing of the two components is performed at time of application.

APPLICATION

Use spray equipment with pump to set high pressure spray-in-place.

Equipment Pressure	1500 psi (min.) (10.3 MPa)
Pre-Heater Temperature	
A Component	120°-140° F (49°-60° C)
B Component	120°-140° F (49°-60° C)

LIMITATIONS

Minimum application temperature of the material is -10° F (-23° C). **DO NOT THIN**, solvents will prevent proper cure.

NOTE

A variety of colors are available upon request.

MATERIAL PROPERTIES

PROPERTY	ASTM METHOD	TYPICAL TEST VALUE	
		TYPE I	TYPE II
Density, pcf (pcm)	ASTM D-1622	70 (2)	70 (2)
Hardness (shore D)	ASTM D-2240	40-45	60
Taber Abrasion Resistance H-22, 1,000 cycles, oz. (mg)	ASTM D-4060	Weight loss 0.0002 (5.7)	
Tensile Strength, psi (MPa)	ASTM D-412	4,000 (27.5)	6,000 (41.4)
Elongation (%)	ASTM D-412	750	350
Young's Modulus, psi (MPa)	ASTM D-412	8,000 (55.2)	30,000 (206.8)
Tear Resistance, psi (MPa)	ASTM D-1004	420 (2.9)	550 (3.8)
Color		Grey	Grey

CURE PROPERTIES

Gel Time	3 - 7 sec.	3 - 7 sec.
Tack Free	10 - 22 sec.	10 - 22 sec.
Final Cure	7 days	7 days

CAUTION!

VAPOR INHALATION

Problems are characterized by coughing, shortness of breath and tightness in the chest. Anyone exhibiting these type of symptoms should be removed from the work area to fresh air. If the condition is prolonged or extreme, seek medical attention immediately.

SKIN CONTACT

Contact with skin may result in a rash or other irritation. Wash any affected skin area with water. Wipe residual liquid from the skin with a clean cloth, then wipe affected area with a 30% solution of rubbing alcohol. Follow the alcohol wipe with repeated washings with soap and water. If a rash or other irritation develops, consult a physician.

EYE CONTACT

Can result in corneal burns or abrasions. In case of eye contact, flush eyes with water for an extensive period. Get medical attention immediately.

DISPOSAL

Do not mix liquid waste components together for disposal convenience as conditions for spontaneous combustion may exist. Dispose of materials in accordance with local, State and Federal disposal regulations.

PROTECTIVE EQUIPMENT

Maximum effort should be made to protect the spray mechanic and others near the work area from undue exposure. Some ingredients in the material may be sensitizing in regards to skin or eye contact.

PROTECTION OF THE WORKPLACE

The foam overspray from the liquid chemical system can carry considerable distances. The following precautions should be taken:

- 1) Post warning signs a minimum of 130 ft. from the immediate work area.
- 2) Cover all intake vents near the work area.
- 3) Set up wind breaks when necessary.
- 4) Minimize or exclude all personnel not directly involved with the spray application.
- 5) DO NOT weld, smoke or allow open flames near the work area.

SHIPPING LABELS CONTAIN

- State specification number with modifications, if applicable
- Component designation
- Type, if applicable
- Manufacturer's name
- Date of manufacture
- Batch name
- State lot number, if applicable
- Directions for use
- Warnings or precautions by law

**KEEP CONTAINER TIGHTLY CLOSED.
NOT FOR INTERNAL CONSUMPTION.
CONSULT MATERIAL SAFETY DATA SHEET
(MSDS) FOR MORE INFORMATION.
KEEP OUT OF REACH OF CHILDREN.
FOR INDUSTRIAL USE ONLY.**

Fyfe Co. LLC

“The Fibrwrap® Company”

Nancy Ridge Technology Center

6310 Nancy Ridge Drive, Suite 103, San Diego, CA 92121

Tel: 858.642.0694 Fax: 858.642.0947

E-mail: info@fyfeco.com Web: <http://www.fyfeco.com>

Statement of Responsibility: The technical information and application advice in this publication is based on the present state of our best scientific and practical knowledge. As the nature of the information herein is general, no assumption can be made as to the product's suitability for a particular use or application, and no warranty as to its accuracy, reliability or completeness, either expressed or implied, is given other than those required by State legislation. The owner, his representative or the contractor is responsible for checking the suitability of products for their intended use. Field service, where provided, does not constitute supervisory responsibility. Suggestions made by the Fyfe Co., either verbally or in writing, may be followed, modified or rejected by the owner, engineer or contractor since they, and not the Fyfe Co., are responsible for carrying out procedure appropriate to a specific application.