

# Tyfo® PR System

## using Tyfo® SEH-51A and Tyfo® S Epoxy

### DESCRIPTION

The Tyfo® PR System is a prefabricated structural casing comprised of the Tyfo® SEH-51A fabric and Tyfo® S Epoxy. Tyfo® SEH-51A is a custom weave, uni-directional glass fabric used in the Tyfo® Fibrwrap System. The glass material is orientated in the 0° direction with additional yellow glass cross fibers at 90°. The Tyfo® S Epoxy is a two-component epoxy matrix material for bonding applications.

### USE

The Tyfo® PR System is designed to add strength and ductility to existing piles. The prefabricated jackets are typically designed to add both vertical stiffness and confinement to wood, reinforced concrete and precast piles. The Tyfo® PR System is installed around the piles by applying the Tyfo® SW-1 Epoxy to the seam and fastening with self-tapping screws. The annular space is then grouted with the required Tyfo® grout for the application.

### ADVANTAGES

- Easy to install
- ICC ER-5282 listed material
- NSF/ANSI Standard 61 listed product for drinking water systems
- Good high & low temperature properties
- 100% solvent-free

### PACKAGING

Varies according to custom fabrication sizes.

### STORAGE CONDITIONS

Store casing at 40° to 90° F (4° to 32° C). Avoid freezing.

### CERTIFICATE OF COMPLIANCE

- Will be supplied upon request, complete with state and federal packaging laws with copy of labels used.
- Material safety data sheets will be supplied upon request.
- Possesses 0% V.O.C. level.

### COMPOSITE CASING PROPERTIES

PROPERTY	ASTM METHOD	TYPICAL TEST VALUE	DESIGN VALUE*
Ultimate tensile strength in primary fiber direction, psi	D-3039	83,400 psi (575 MPa) (4.17 kip/in. width)	66,720 psi (460 MPa) (3.3 kip/in. width)
Elongation at break	D-3039	2.2%	1.76%
Tensile Modulus, psi	D-3039	3.79 x 10 <sup>6</sup> psi (26.1 GPa)	3.03 x 10 <sup>6</sup> psi (20.9 GPa)
Ultimate tensile strength 90 degrees to primary fiber, psi	D-3039	3,750 psi (25.8 MPa)	3,000 psi (20.7 MPa)
Laminate Thickness per layer		0.05 in. (1.3 mm)	0.05 in. (1.3mm)

\* Typical jacket designs consist of two layers oriented vertically and one layer oriented horizontally. The additional structural performance will depend on the existing pile size and capacity. Contact Fyfe Co. LLC engineers for design and technical assistance.

### HOW TO USE THE TYFO® PR SYSTEM

#### DESIGN

The Tyfo® PR System shall be designed to meet specific design criteria. The criteria for each project is dictated by the engineer of record and any relevant building codes and/or guidelines. The design should be based on the allowable strain for each type of application and the design modulus of the material. The Fyfe Co. LLC engineering staff will provide preliminary design at no obligation.

#### INSTALLATION

Tyfo® PR System to be installed by Fyfe Co. LLC trained and certified applicators. Installation shall be in strict compliance with the Fyfe Co. LLC Quality Control Manual.

#### SURFACE PREPARATION

The required surface preparation is largely dependent on the type of element being strengthened. In general, the surface must be relatively clean and free of protrusions. The Fyfe Co. LLC engineering staff will provide the proper specifications and details based on the project requirements.

#### APPLICATION

The Tyfo® PR System is installed around the piles by applying the Tyfo® SW-1 Epoxy to the seam and fastening with self-tapping screws. The annular space is then grouted with the required Tyfo® grout for the application.

### CAUTION!

#### SAFETY PRECAUTIONS

Gloves are recommended when handling prefabricated composite jackets.

#### SHIPPING LABELS CONTAIN

- State specification number with modifications, if applicable
- Component designation
- Type, if applicable
- Manufacturer's name
- Date of manufacture
- Batch name
- State lot number, if applicable
- Directions for use
- Warnings or precautions by law

**CONSULT MATERIAL SAFETY DATA SHEET (MSDS) FOR MORE INFORMATION. KEEP OUT OF REACH OF CHILDREN. FOR INDUSTRIAL USE ONLY.**

**Fyfe Co. LLC**

“The Fibrwrap® Company”

Nancy Ridge Technology Center

6310 Nancy Ridge Drive, Suite 103, San Diego, CA 92121

Tel: 858.642.0694 Fax: 858.642.0947

E-mail: [info@fyfeco.com](mailto:info@fyfeco.com) Web: <http://www.fyfeco.com>

**Statement of Responsibility:** The technical information and application advice in this publication is based on the present state of our best scientific and practical knowledge. As the nature of the information herein is general, no assumption can be made as to the product's suitability for a particular use or application, and no warranty as to its accuracy, reliability or completeness, either expressed or implied, is given other than those required by State legislation. The owner, his representative or the contractor is responsible for checking the suitability of products for their intended use. Field service, where provided, does not constitute supervisory responsibility. Suggestions made by the Fyfe Co., either verbally or in writing, may be followed, modified or rejected by the owner, engineer or contractor since they, and not the Fyfe Co., are responsible for carrying out procedure appropriate to a specific application.